



COSENTINO®
imagine & anticipate

TECHNICAL INFORMATION

DEKTON

Name and Identification

Product: Dekton®

Code: Family II

(Zenith, Aura, Ariane, Kairos)

Name and address of manufacturer:

Company: Cosentino S.A

Address: Carretera A-334, km 59, código postal 04850 Cantoria (Almería) - Spain

TECHNICAL INFORMATION DEKTON FAMILY II

STANDARD EN-14411

Test	Standard	Determination	UD	Family II
Flexural tensile strength or modulus of rupture	EN ISO 10545-4	Average flexural resistance	N/mm ²	67
		Average break load	N	2,313
		Average break strength	N	13,559
Water absorption, apparent porosity, density	EN ISO 10545-3	Water absorption by boiling	%	0.1
		Water absorption by vacuum	%	0.1
		Open porosity	%	0.2
		Apparent relative density	g/cm ³	2.61
		Apparent density	g/cm ³	2.61
Resistance to deep abrasion	EN ISO 10545-6	Wear volume	mm ³	106
Dimensions and surface quality	EN ISO 10545-2	Length and width	%	0.04/-0.08
		Thickness	%	4.95/-2.20
		Straightness of sides	%	0.03/-0.03
		Rectangularity	%	0.04/-0.09
		Centre curvature	%	-0.06
		Side curvature	%	0.02/-0.04
		Warping	%	-0.07
Surface quality	%	100		
Impact resistance	EN ISO 10545-5	Coefficient of restitution (COR)	-	0.85
Determination of linear thermal expansion	EN ISO 10545-8	Expansion 30-100°C	°C ⁻¹	5.1·10 ⁻⁶
Thermal shock resistance	EN ISO 10545-9	Damage	-	No affected
Moisture expansion	EN ISO 10545-10	Expansion max	mm/m	0.1
		Expansion mid	mm/m	0.0
Frost resistance	EN ISO 10545-12	Damage	-	No affected
Resistance to chemicals	EN ISO 10545-13	CINH ₄ / Cleaning products	Type	UA (no damage)
		Bleach/swimming pool salts	Type	UA (no damage)
		HCl (3% v/v)	Type	ULA (no damage)
		Citric acid (100 g/l)	Type	ULA (no damage)
		KOH (30 g/l)	Type	ULA (no damage)
		HCl (18%)	Type	ULA (no damage)
		Lactic acid (5%)	Type	ULA (no damage)
KOH (100 g/l)	Type	ULA (no damage)		
Resistance to staining	EN ISO 10545-14	Green agent	Type	5
		Red agent	Type	-
		Iodine (solution)	Type	5
		Olive oil	Type	5

SLIPPERINESS DEKTON FAMILY II

STANDARD EN-14231

Finishing	Color	Determination	Value
Natural	Zenith Aura Kairos	USRV dry	48
		USRV humid	23
Wood-like	Ariane	USRV dry	44
		USRV humid	21

ACCORDING TO DIN 51130 AND DIN 51097 STANDARDS

Finishing	Color	Norm	Value (°)	Class
Natural	Zenith Aura Kairos	DIN 51130	7,2	R9 -
		DIN 51097	8	
Wood-like	Ariane	DIN 51130	5,7	- A
		DIN 51097	14	